

Distributed by:



Lubrication properties

LY13

Lubrication type	Grease
Color	Semitransparency
Thickener type	Li soap
Base oil type	Methyl phenyl silicone
Base oil viscosity	80 (mm ² /S) 40Deg.C
Worked penetration	260 (25 Deg.C 60W)
Drop point	210 (Deg.C)
Useful operating temperature range	-40 to 180 (Deg.C)