

NMB

Distributed by:



Pacific International Bearing

800.228.8895

www.pibsales.com

Lubrication properties

LY308

Lubrication type	Grease
Color	
Thickener type	PTFE
Base oil type	PFPE
Base oil viscosity	110~170 (mm² /S) 40Deg.C
Worked penetration	270~295 (25 Deg.C 60W)
Drop point	182 (Deg.C)
Useful operating temperature range	-80 to 200 (Deg.C)