



Distributed by:



Pacific International Bearing
800.228.8895
www.pibsales.com

Lubrication properties

LY75

Lubrication type	Grease
Color	Dark Green
Thickener type	Polyurea
Base oil type	Mineral
Base oil viscosity	116 (mm ² /S) 40Deg.C
Worked penetration	280 (25 Deg.C 60W)
Drop point	243 (Deg.C)
Useful operating temperature range	-29 to 177 (Deg.C)